

H.B.plus BANDAMATIC



OTR



COMPOUND	ACC-3006	GCR-687	OTR-684	OTR-680	OTR-670	OTR-667	OTR-637	GRADER T	SIDE WALL	SHOULDER
POLYMER CONTENT										
Natural	100	80	100	100	50	100	70	10	50	100
Synthetic		20			50		30	90	50	
PHYSICAL PROPERTIES										
Tensile Psi	3000	2800	2500	2400	2250	2900	2900	1800	2000	2400
Modulus 300% Psi	1700	1200	1100	1000	1000	1100	1100	1000	400	800
Elongation %	500	500	500	300	500	500	500	450	550	500
Hardness Shore A	67	67	66	80	67	66	66	61	54	62
Specific Gravity	1.150	1.140	1.135	1.160	1.150	1.130	1.140	1.130	1.080	1.140
Min. Tc90 @ 302 °F	20	20	20	23	15	20	20	20	17	17
MAIN FEATURES										
Cut Chipping Resistance	Excellent	High	Excellent	Excellent	Good	Excellent	High	Good	High	High
Aging Resistance	High	High	High	High	High	High	High	High	High	High
Green Tack	High	Good	High	High	Good	High	Good	Good	Good	Excellent
FORM										
Slab	✓	✓	✓	✓	✓	✓	✓	✓	ROLL	ROLL
Strip	✓	✓	✓	✓	✓	✓	✓	✓		
Lug	✓	✓	✓	✓	✓	✓	✓	✓		
MAIN USE										
Sculpture	✓	✓	✓	✓	✓	✓	✓	✓		
Open Steam	✓	✓	✓	✓	✓	✓	✓	✓		
Mold	✓	✓	✓	✓	✓	✓	✓	✓		
TIRE APPLICATIONS										
Loader	✓	✓	✓	✓	✓	✓	✓	✓		
Haul	✓	✓	✓	✓	✓	✓	✓	✓		
Underground Mine										
Grader								✓		



SPECIAL DESIGNED OTR COMPOUNDS WITH AN OUTSTANDING PERFORMANCE UNDER THE MOST SEVERE TERRAIN CONDITIONS

Phone. (281)821-9719
 Fax. (281)821-5562
 Toll Free USA 1-866-704-8537

E-mail: hq@hbplusbandamatic.com

www.hbplusbandamatic.com

